

昌 葧 股 份 有 限 公 司 Dr. POWER CORPORATION

零件規格書/承認書 SPECIFICATION FOR APPROVAL

CUSTOMER :					
DESCRIPTION : <u>Battery Pack</u>					
MODEL:	MODEL:				
CUSTOMER PA	RT NO :				
	APPROVED SIGNATURES				

Rev	Date	Description	Designed	Checked	Approved
Α	2019/12/9	Release		Kevin	

臺北市北投區吉利街 131 號 3 樓

3F, NO. 131, JILI ST., PEITOU, TAIPEI, TAIWAN, R.O.C.

TEL: 886-2-2820-7419 · FAX: 886-2-2827-0348

Specification

Revision History(版本紀錄 / 版本纪录)

Revision	Description	Written Date	Remark
版本 / 版本	內容 / 內容	日期 / 日期	備註 / 备注
V0.1	Design Start	2017.06.20	
V0.3	Addition Product Remark	2017.10.20	
V0.4	Addition Charge Remark	2017.01.05	
V0.5	Update Over Temp. of Charge Protect	2018.02.26	
V1.0	Update Label Drawing	2019.12.06	

Specification

Contents(內容/內容)

1.	Scope(用途 / 用途)	4
2.	Name and Model(廠商與型號 / 厂商与型号)	4
3.	Product Specification(產品規格 / 产品规格)	4
4.	Protection Function of Protect IC(保護版規格 / 保护板规格)	4
5.	Protection Function of Permanent Fail(永久性失效 /永久性失效)	5
6.	Connect Pin Define(連接器定義 / 连接器定义)	5
7.	Schematic(線路圖 / 线路图)	6
8.	Mechanism Drawing(機構圖 / 机构图)	7
9.	Conncet Spec.(連接器規格 / 连接器规格)	9
10.	. Label Drawing(標籤 / 标签)	10
11.	. Cell ICR 18650-26J Spec.(Cell 規格 / Cell 规格)	11
12.	Fuel Gauge BQ40z50-R1 Spec.(BQ40z50-R1 規格 / BQ40z50-R1 规格)	30

OUR MODEL	DR-202V2	Date	2018/4/13
OUR P/N	-	Rev.	1.0

1. Scope

This specification shall be applied to the lithium battery to be supplied by . The battery pack is use for Tablet Products

2. Name and Model

Customer Model Name:

Model Name: DR-202V2
Cell Type: ICR 18650-26J

Cell Configuration: 3S-3P

3. Product Specification

No	Item	Rate performance	Remark
1	Typical capacity	Above 7800 mAh	Charge: 12.6V / 2.6A / cut off current 0.2A Discharge: 2.6A / cut off voltage 7.5V
2	Normal voltage	11.1 V	
3	Charge voltage	12.6 V	When battery detect charge voltage > 12.3V & charge current < 400mA, the RSOC will update 100%
4	End voltage	9 V	System cut off voltage
5	Continuous charge current	5 A	Suggest charge current
6	Continuous discharge current	5 A	Discharge Power < 55.5W at 40°C
7	Maximum discharge current	7 A	Discharge Power < 77.7W at 25°C
0	0	Charge 0~45°C	Protect release temperature 5~45°C
δ	Operation temperature	Discharge -10~60°C	Protect release temperature -5~55°C
9	Storage temperature	0~40 °C	Storage less than 3 months
10	Cycle life	300 cycle > 6240	Capacity after 299 cycles at 25°C
11	Internal impedance	$<$ 180m Ω	
	Power consumption		
12	normal mode sleep mode shutdown mode	$\leq 300 \mu\mathrm{A}$	

4. Protection Function of Protect $IC(Ta = 25 \, ^{\circ}C)$

Function item	Control function and operation	Remark
Over charge detection voltage	$4.25 \pm 0.01 \text{ V}$	Anyone cell voltage over 4.25V will protect
Over charge delay time	1~3 Sec	
Over charge release voltage	4 ± 0.1 V	Protect release need all cell voltage under 4V
Over discharge detection voltage	$2.8 \pm 0.1 \text{ V}$	Anyone cell voltage over 2.8V will protect
Over discharge delay time	2~4 Sec	
Over discharge release voltage	$3.2 \pm 0.1 \text{ V}$	Protect release need all cell voltage over 3.2V
Over charge prohibition current	5.6 ± 1 A	
Over charge prohibition delay time	2~4 Sec	
Over discharge prohibition current 1 st	$7.5 \pm 1 \text{ A}$	Software protection
Over discharge prohibition 1 st delay time	4~7 Sec	
Over discharge prohibition current 2 nd	$8.8 \pm 1 \text{ A}$	Software protection
Over discharge prohibition 2 nd delay time	2~4 Sec	
Hardware discharge prohibition current	25 ± 1 A	Hardware protection
Over discharge prohibition 2 nd delay time	4~7 mSec	


Short protection delay time	122 ± 300 uSec	Hardware protection
Over temperature of charge	50 ± 3 °C	
Delay of charge over temperature	2~4 Sec	
Release temperature of charge	45 ± 3 °C	
Over temperature of discharge	60 ± 3 °C	
Delay of discharge over temperature	2~4 Sec	
Release temperature of discharge	55 ± 3 °C	
Under temperature of charge	0 ± 3 °C	
Delay of charge under temperature	2~4 Sec	
Release temperature of charge	5 ± 3 °C	
Under temperature of discharge	-10 ± 3 °C	
Delay of discharge under temperature	2~4 Sec	
Release temperature of discharge	-5 ± 3 °C	


5. Protection Function of Permanent Fail(Non-recoverable)


Function Item	Control Function and Operation	Remark
Over charge detection voltage	Anyone cell ≥ 4.4 V	15 Sec
Over Temperature Protect	Mosfet Temp ≥ 85°C	5 Sec
Over Temperature Protect	Cell Temp ≥ 75°C	10 Sec
FET Failure	C-FET cut off & current > 150 mA	10 Sec
FET Famule	D-FET cut off & current > -150 mA	TO Sec


6. Connect Pin Define

Name	Function	Remark
1	P+	
2	SMBus Clock	
3	SMBus Data	
4	ID	390Ω connect to P-
5	P-	









LI-ION RECHARGEABLE BATTERY PACK

MODEL: DR-202V2

DC 11.1V 7800mAh 87Wh

Japone Technology Inc.

3ICR19/66-3

Made in Taiwan

CAUTION!

When damaged, replace only with the same or equivalent type of battery pack recommended by the manufacturer. Do not attempt to open. Danger of explosion if battery is incorrectly placed near heat source or immerse in liquid. Any misuse of battery pack could cause fire, explosion and personal injury.

ATTENTION

Maintenez la batterie éloignée de toute flamme. Évitez de la mettreen court-circuit.

N'essayez jamais de démonter la batterie. Utilisezles chargeurs prévus pour charger la batterie.

Risque d'explosion si la batterie est remplacée par un type incorrect.


Eliminez les batteries usagées conformément aux instructions.

警告!

電池損壞時,請更換與原廠規格相等的電池.

請勿打開電池外殼,且不要暴露於高溫、高熱處,不可放入液體中.

假如誤用可能會引起燃燒 、爆炸或傷及人體.















Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

SPECIFICATION OF PRODUCT

for Lithium-ion Rechargeable Cell

Model: ICR18650-26J

Apr 1st 20167

Samsung SDI Co.,Ltd.

Battery Business Division



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Revision history

Revision No.	Date('yr-m-d)	Page	Item	Description	Changes / Author
V 0.0	′14-09-11		First version		Jongsik Jung
V 1.0	′14-10-16			First Edition_General	Kwangsoo Kim
V 1.1	′15-01-07	6	Storage Characteristics	Typo correction	Mark Min
		2	3. Note (1) Ex-factory status	50% → 30%	
V1.2	'16-04-01 6	6	7.10 Ex-factory status	3.55V~3.75V→3.53V~3.63V	Lucy Kim



Spec. No. ICR18650-26J	Version No.	1.2
------------------------	-------------	-----

1. Scope

This product specification has been prepared to specify the rechargeable lithium-ion cell ('cell') to be supplied to the customer by Samsung SDI Co., Ltd.

2. Description and Model

2.1 Description Cell (lithium-ion rechargeable cell)

2.2 Model ICR18650-26J

2.3 Site Manufactured in Korea & Malaysia

3. Nominal Specifications

ltem	Specification
3.1 Nominal Capacity	2600mAh (0.2C, 2.75V discharge)
3.2 Minimum Capacity	2550mAh(0.2C, 2.75V discharge)
3.3 Charging Voltage	4.2 ±0.05 V
3.4 Nominal Voltage	3.63V
3.5 Charging Method	CC-CV (constant voltage with limited current)
3.6 Charging Current	Standard charge: 1300mA Rapid charge : 2600mA
3.7 Charging Time	Standard charge : 3hours Rapid charge : 2.5hours
3.8 Max. Charge Current	2600mA(ambient temperature 25 $^{\circ}\mathrm{C}$)
3.9 Max. Discharge Current	5200mA(ambient temperature 25℃)
3.10 Discharge Cut-off Voltage	2.75V
3.11 Cell Weight	45.0g max
3.12 Cell Dimension	Height : 65.00mm max Diameter : 18.40mm max
3.13 Operating Temperature	Charge : 0 to 45 $^{\circ}{\mathbb C}$ Discharge: -10 to 60 $^{\circ}{\mathbb C}$
3.14 Storage Temperature	1 year : -20~25 ℃ (1*) 3 months : -20~45 ℃ (1*) 1 month : -20~60 ℃ (1*)

Note (1): If the cell is kept as ex-factory status (30% of charge), the capacity recovery rate is more than 80%.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

4. Outline Dimensions

See the Fig. 1




Fig.1. Outline Dimensions of ICR18650-26J



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

5. Appearance

There shall be no such defects as scratch, rust, discoloration, leakage which may adversely affect commercial value of the cell.

6. Standard Test Conditions

6.1 Environmental Conditions

Unless otherwise specified, all tests stated in this specification are conducted at temperature $25\pm5^{\circ}$ °C and humidity 65 ± 20 %.

6.2 Measuring Equipment

(1) Ammeter and Voltmeter

The ammeter and voltmeter should have an accuracy of the grade 0.5 or higher.

(2) Slide caliper

The slide caliper should have 0.01 mm scale.

(3) Impedance meter

The impedance meter with AC 1kHz should be used.

7. Characteristics

7.1 Standard Charge

This "Standard Charge" means charging the cell with charge current 1300mA and constant voltage 4.2V at 25 $^{\circ}$ C for 3hours.

7.2 Standard Discharge Capacity

The standard discharge capacity is the initial discharge capacity of the cell, which is measured with discharge current of 520mA with 2.75V cut-off at 25 $^{\circ}$ C within 1hour after the standard charge.

Standard Discharge Capacity ≥ 2550mAh

7.3 Initial internal impedance

Initial internal impedance measured at AC 1kHz after rated charge.

Initial internal impedance \leq 100m Ω

7.4 Temperature Dependence of Discharge Capacity

Capacity comparison at each temperature, measured with discharge constant current 520mA and 2.75V cut-off after the standard charge is as follows.

Charge Temperature	Discharge temperature			
25 ℃	-10℃	0℃	25 ℃	40℃
Relative Capacity	50%	70%	100%	80%

Note: If charge temperature and discharge temperature is not the same, the interval for temperature change is 3 hours.

Percentage as an index of the capacity at 25 $^{\circ}$ (=2550mAh) is 100%.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

7.5 Temperature Dependence of Charge Capacity

Capacity comparison at each temperature, measured with discharge constant current 520mA and 2.75V cut-off after the standard charge is as follows.

	Charge temperature			Discharge temperature
	0℃	25 ℃	45℃	25℃
Relative Capacity	80%	100%	80%	25 0

Note: If charge temperature and discharge temperature is not the same, the interval for temperature change is 3 hours.

Percentage as an index of the capacity at 25 °C (=2550mAh) is 100%.

7.6 Charge Rate Capabilities

Discharge capacity is measured with constant current 520mA and 2.75V cut-off after the cell is charged with 4.2V as follows.

	Charge Condition			
Current	1.0C (2600mA)	2.0C (5200mA)		
Cut-off	2.5h or 0.05C	2.5h or 0.05C		
Relative Capacity	90%	80%		

Note: Percentage as an index of the capacity at 25° C (=2550mAh) is 100%.

7.7 Discharge Rate Capabilities

Discharge capacity is measured with the various currents in under table and 2.75V cut-off after the standard charge.

	Discharge Condition					
Current	0.2C (520mA)	0.5C (1300mA)	1.0C (2600mA)	2.0C (5200mA)		
Relative Capacity	100%	95%	90%	80%		

Note: Percentage as an index of the capacity at 25 °C (=2550mAh) is 100%.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

7.8 Cycle Life

Each cycle is an interval between the charge (charge current 1300mA) with 2.5h or 0.05C cut-off and the discharge (discharge current 1300mA) with 2.75V cut-off. Capacity after 299cycles and plus 1 day, measured under the same condition in 7.2

Capacity \geq 1785mAh(70% of the capacity at 25°C)

7.9 Storage Characteristics

Capacity after storage for 30days at 25 $^{\circ}$ C from the standard charge, measured with discharge current 520mA with 2.75V cut-off at 25 $^{\circ}$ C.

Capacity retention(after the storage) ≥ 2040mAh (80% of the capacity at 25 °C)

7.10 Status of the cell as of ex-factory

The cell should be shipped in 3.53V ~ 3.63V Charging voltage range.

8. Mechanical Characteristics

8.1 Drop Test

Test method: Cell(as of shipment or full charged) drop onto the oak-board (thickness: ≥ 30mm) from 1.5m height at a random direction 6 times.

Criteria: No leakage

8.2 Vibration Test

Test method: Cell(as of shipment) is vibrated along 2 mutually perpendicular axes with total excursion of 1.6mm and with frequency cycling between 10Hz and 55Hz by 1Hz/min.

Criteria: No leakage

9. Safety

9.1 Overcharge Test

Test method: To charge the standard charged cell with 12V and 2.6A at $25\,^{\circ}$ C for 2.5 hours.

Criteria: No fire, and no explosion.

9.2 External Short-circuit Test

Test method: To short-circuit the standard charged cell by connecting positive and negative terminal by $60{\sim}100m\Omega$ wire for 3hours.

Criteria: No fire, and no explosion.

9.3 Reverse Charge Test

Test method: To charge the standard charged cell with charge current 2.6A By -12V for 2.5 hours.

Criteria: No fire, and no explosion.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

9.4 Heating Test

Test method: To heat up the standard charged cell at heating rate 5 ℃ per minute up to 130 ℃ and keep the cell in oven for 10 minutes.

Criteria: No fire, and no explosion.

10. Warranty

Samsung SDI will be responsible for replacing the cell against defects or poor workmanship for 15months from the date of shipping. Any other problem caused by malfunction of the equipment or mix-use of the cell is not under this warranty.

The warranty set forth in proper using and handling conditions described above and excludes in the case of a defect which is not related to manufacturing of the cell.

11. Others

11.1 Storage for a long time

If the cell is kept for a long time(3months or more), It is strongly recommended that the cell is preserved at dry and low-temperature.


11.2 Other

Any matters that specifications does not have, should be conferred with between the both parties.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

12. PackingSee Fig.2,
Package Drawing



NO	PART NAME	MATERIAL	MATERIAL DIM	Q'TY	TREATMENT
01	INR18650 (Ref. Model List)	BARE CELL	≢18, H65	200	NONE
02	PACKING GUIDE	MANILA	L192×W191×H67	200	NONE
03	PACKING CASE IN	SW-1(B FLUTE)	L192×W192×H68	2	NONE
04	SILICAGEL	SI	L50×W50,3G	2	NONE
05	PE BAG(LARGE)	PE	L500×W450×T0.028	1	NONE
06	TAPE	PE(OPP)	W50×T0.05	1	NONE
07	PACKING CASE OUT	DW-1(BA FLUTE)	L225×W214×H164	1	NONE
08	LABEL	ART PAPER	L52×W100	1	NONE

Fig.2. Package Drawing



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Proper Use and Handling of Lithium Ion Cells

See before using lithium-ion cell Supplied by Samsung SDI Co., Ltd.

1. General

This document has been prepared to describe the appropriate cautions and prohibitions, which the customer should take or employ when the customer uses and handles the lithium ion cell to be manufactured and supplied by Samsung SDI Co., Ltd., in order to obtain optimum performance and safety.

2. Charging

2.1 Charging current

Charging current should be less than maximum charge current specified in the product specification.

2.2 Charging voltage

Charging should be done by voltage less than that specified in the product specification.

2.3 Charging time

Continuous charging under appropriate voltage does not cause any loss of characteristics. However, the charge timer is recommended to be installed from a safety consideration, which shuts off further charging at time specified in the product specification.

2.4 Charging temperature

The cell should be charged within a range of specified temperatures in the product specification.

2.5 Reverse charging

The cell should be connected, confirming that its poles are correctly aligned. Inverse charging should be strictly prohibited. If the cell is connected improperly, it may be damaged.

3. Discharging

3.1 Discharging

3.1.1 The cell should be discharged at less than maximum discharge current specified in the product specification.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

3.2 Discharging temperature

- 3.2.1 The cell should be discharged within a range of temperatures specified in the product specification.
- 3.2.2 Otherwise, it may cause loss of characteristics.

3.3 Over-discharging

- 3.3.1 The system should equip with a device to prevent further discharging exceeding discharging cut-off voltage specified in the product specification.(over-discharging)
- 3.3.2 Over-discharging may cause loss of performance, characteristics, of battery function.
- 3.3.3 Over-discharging may occur by self-discharge if the battery is left for a very long time without any use.
- 3.3.4 The charger should equip with a device to detect cell voltage and to determine recharging procedures.

4. Storage

4.1 Storage conditions

- 4.1.1 The cell should be stored within a range of temperatures specified in the product specification.
- 4.1.2 Otherwise, it may cause loss of characteristics, leakage and/or rust.

4.2 Long-term storage

- 4.2.1 The cell should be used within a short period after charging because long-term storage may cause loss of capacity by self-discharging.
- 4.2.2. If long-term storage is necessary, the cell should be stored at lower voltage within a range specified in the product specification, because storage at higher voltage may cause loss of characteristics.

5. Cycle life

5.1 Cycle life performance

- 5.1.1 The cell can be charged/discharged repeatedly up to times specified in the produce specification with a certain level of capacity also specified in the product specification.
- 5.1.2 Cycle life may be determined by conditions of charging, discharging, operating temperature and/or storage.

6. Design of System

- 6.1 Connection between the cell and the battery
 - 6.1.1 The cell should not be soldered directly with leads. Namely, the cell should be welded with leads on its terminal and then be soldered with wire or leads to soldered lead.



1.2
_

6.1.2 Otherwise, it may cause damage of component, such as separator and insulator, by heat generation.

6.2 Positioning the battery in the System

- 6.2.1 The battery should be positioned as possible as far from heat sources and high temperature components.
- 6.2.2 Otherwise, it may cause loss of characteristics.

6.3 Mechanical shock protection of the battery

- 6.3.1 The battery should equip with appropriate shock absorbers in order to minimize shock.
- 6.3.2 Otherwise, it may cause shape distortion, leakage, heat generation and/or rupture.

6.4 Short-circuit protection of the cell

- 6.4.1 The cell equips with an insulating sleeve to protect short-circuit which may occur during transportation, battery assembly and /or system operation.
- 6.4.2 If the cell sleeve is damaged by some cause such as outside impact, it may cause short-circuit with some wiring inside the battery.

6.5 Connection between the battery and charger/system

- 6.5.1 The battery should be designed to be connected only to the specified charger and system.
- 6.5.2 A reverse connection of the battery, even in the specified system, should be avoided by employing special battery design such as a special terminals.

7. Battery Pack Assembly

7.1 Prohibition of usage of damaged cell

- 7.1.1 The cell should be inspected visually before battery assembly.
- 7.1.2 The cell should not be used if sleeve-damage, can-distorsion and/or electrolyte-smell is detected.

7.2 Terminals handling

7.2.1 Excessive force on the negative terminal should be avoided when external lead is welled.

7.3 Transportation

7.3.1 If the cell is necessary to transported to order place, such as the battery manufacturer, careful precautions should be taken to avoid damage of cell.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

8. Others

8.1 Disassembly

- 8.1.1 The cell should not be dismantled from the battery pack.
- 8.1.2 Internal short-circuit caused by disassembly may lead to heat generation and/or venting.
- 8.1.3 When the electrolyte is coming in contact with the skin or eyes, flush immediately with fresh water and seek medical advice.

8.2 Short-circuiting

- 8.2.1 Short-circuit results in very high current which leads to heat generation.
- 8.2.3 An appropriate circuitry should be employed to protect accidental short-circuiting.

8.3 Incineration

8.3.1 Incinerating and disposing of the cell in fire are strictly prohibited, because it may cause rupture.

8.4 Immersion

8.4.1 Soaking the cell in water is strictly prohibited, because it may cause melt of components to damaged to functions.

8.5 Mixing use

8.5.1 Different types of cell, or same types but different manufacturer's cell may lead to cell rupture or damage to system due to the different characteristics of cell.

8.6 Battery exchange

- 8.6.1 Although the cell contains no environmentally hazardous component, such as lead or cadmium. the battery should be disposed according to the local regulations when it is disposed.
- 8.6.2 The cell should be disposed with a discharged state to avoid heat generation by an inadvertent short-circuit.
- 8.7 Caution The Battery used in this device may present a risk of fire or chemical burn if mistreated. Do not disassemble, heat above 100°C or incinerate. Replace battery with Samsung SDI battery only. Use of another battery may present a risk of fire or explosion. Dispose of used battery promptly. Keep away from children. Do not disassemble and do not dispose of in fire.

8.8 Warning – Attached



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Pack Design Guideline (For electrical design)

	Item	Portable IT	Power-Tool	Medical	E-Bike	E-Scooter	EV/LEV	ESS/UPS
☐ Standard charging voltage (4.20V cell)		4.20V	4.20V	4.10V	4.10V	4.10V	4.10V	4.00V (4.05V)
☐ Stand	dard charging voltage (4.35V cell)	4.35V	4.35V	4.20V	4.20V	4.20V	4.20V	4.00V (4.05V)
☐ Char	ging method	CC-CV						
☐ Full-c	charging cut-off current*	0.05C	0.05C	0.025C	0.025C	0.025C	0.025C	0.025C (Continous)
☐ Volta	☐ Voltage of Re-charging (4.20V cell)		4.10V	4.05V	4.05V	4.05V	4.05V	4.00V (4.05V)
☐ Volta	☐ Voltage of Re-charging (4.35V cell)		4.25V	4.10V	4.10V	4.10V	4.10V	4.00V (4.05V)
LCO	☐ Min. voltage of terminate discharging	3.00V	2.50V	3.00V	3.00V	3.00V	3.00V	3.00V
LMO	☐ Min. voltage of over-discharging protection	2.50V	2.00V	2.50V	2.50V	2.50V	2.50V	2.50V
NCA	☐ Min. voltage of terminate discharging	2.50V						
NCM	☐ Min. voltage of over-discharging protection	2.30V	2.00V	2.50V	2.50V	2.50V	2.50V	2.50V
☐ BMS	Shut Down Voltage**	2.00V						
	consumption current of BMS shut down	10μA/Cell						
☐ Do not charge***		↓ 1.00V						
☐ Pre-c	harging voltage range****	1.0V ~ 3.0V						
☐ Curre	ent range of Pre-charging	0.1C ~ 0.5C						

Remark:

- * Current of cell which full-charging shall be terminated.
- ** Voltage condition of BMS which shall be shut down.
- *** Under 1.0V voltage, do not charge the cell.
- **** Voltage range of cell which shall be charged by Pre-charging.

If a customer's battery pack cannot meet the requirements above, SDI cannot take responsibility for a quality issue about a battery cell.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

■ Pack Design Guideline (For mechanical design)

ltem	Portable IT	Power-Tool	Medical	E-Bike	E-Scooter	EV/LEV	ESS/UPS
☐ Need partitions(separator) between BMS and a Cell	0	0	0	0	0	0	0
Need to check if the pack is designed to be able to avoid thermal runaway (1KWh ↑)					0	0	0
☐ Need to analyze the battery pack's thermal distribution and its effect on the pack's life cycle					0	©	©
☐ Need to use a non-flammable (VO level) case	©	0	0	0	0	©	©
☐ Need to apply improved material (Steel) to the case						©	©
☐ Need to analyze the battery pack's structure, system, installation status and use environment						0	0

If a customer's battery pack cannot meet the requirements above, SDI cannot take responsibility for a quality issue about a battery cell.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Handling Precaution and Prohibitions of Lithium Ion & Lithium Ion Polymer Rechargeable Cells and Batteries

Inaccurate handling of lithium ion and lithium ion polymer rechargeable battery may cause leakage, heat, smoke, an explosion, or fire.

This could cause deterioration of performance or failure. Please be sure to follow instructions carefully.

1.1 Storage

Store the battery at low temperature (below $20\,^{\circ}$ C is recommended), low humidity, no dust and no corrosive gas atmosphere.

1.2 Safety precaution and prohibitions

To assure product safety, describe the following precautions in the instruction manual of the application.

[Danger!]

Electrical misusage

Use dedicated charger.

Use or charge the battery only in the dedicated application.

Don't charge the battery by an electric outlet directly or a cigarette lighter charger.

Don't charge the battery reversely.

■ Environmental misusage

Don't leave the battery near the fire or a heated source.

Don't throw the battery into the fire.

Don't leave, charge or use the battery in a car or similar place where inside of temperature may be over $60\,^{\circ}$ C.

Don't immerse, throw, wet the battery in water / seawater.

others

Don't fold the battery cased with laminated film such as pouch and Polymer.

Don't store the battery in a pocket or a bag together with metallic objects such as keys, necklaces, hairpins, coins, or screws.

Don't short circuit (+) and (-) terminals with metallic object intentionally.

Don't pierce the battery with a sharp object such as a needle, screw drivers.

Don't heat partial area of the battery with heated objects such as soldering iron.

Don't hit with heavy objects such as a hammer, weight.

Don't step on the battery and throw or drop the battery on the hard floor to avoid mechanical shock.

Don't disassemble the battery or modify the battery design including electric circuit.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Don't solder on the battery directly.

Don't use seriously scared or deformed battery.

Don't put the battery into a microwave oven, dryer ,or high-pressure container.

Don't use or assemble the battery with other makers' batteries, different types and/or models of batteries such as dry batteries, nickel-metal hydride batteries, or nickel-cadmium batteries.

Don't use or assemble old and new batteries together.

[Warning!]

Stop charging the battery if charging isn't completed within the specified time.

Stop using the battery if the battery becomes abnormally hot, order, discoloration, deformation, or abnormal conditions is detected during use, charge, or storage.

Keep away from fire immediately when leakage or foul odors are detected. If liquid leaks onto your skin or cloths, wash well with fresh water immediately.

If liquid leaking from the battery gets into your eyes, don't rub your eyes and wash them with clean water and go to see a doctor immediately.

If the terminals of the battery become dirty, wipe with a dry cloth before using the battery.

The battery can be used within the following temperature ranges. Don't exceed these ranges.

Charge temperature ranges : 0° C ~ 45° C

Discharge Temperature ranges : -20° C $\sim 60^{\circ}$ C

Store the battery at temperature below 60 °C

Cover terminals with proper insulating tape before disposal.

[Caution!]

Electrical misusage

Battery must be charge with constant current-constant voltage (CC/CV).

Charge current must be controlled by specified value in Cell specification.

Cut-off Voltage of charging must be 4.2V.

Charger must stop charging battery by detecting either charging time or current specified in Cell's specification.

Discharge current must be controlled by specified value in Cell's specification.

Cut-off Voltage of discharging must be over 2.5V.

others

Keep the battery away from babies and children to avoid any accidents such as swallow.

If younger children use the battery, their guardians should explain the proper handling method and precaution before using.



Spec. No.	ICR18650-26J	Version No.	1.2
-----------	--------------	-------------	-----

Before using the battery, be sure to read the user's manual and precaution of it's handling.

Before using charger, be sure to read the user's manual of the charger.

Before installing and removing the battery from application, be sure to read user's manual of the application.

Replace the battery when using time of battery becomes much shorter than usual.

Cover terminals with insulating tape before proper disposal.

If the battery is needed to be stored for an long period, battery should be removed from the application and stored in a place where humidity and temperature are low.

While the battery is charged, used and stored, keep it away from object materials with static electric chargers.

Safety Handling Procedure for the Transporter

- Quarantine: Packages that are crushed, punctured or torn open to reveal contents should not be transported. Such packages should be isolated until the shipper has been consulted, provided instructions and, if appropriate, arranged to have the product inspected and repacked.
- Spilled Product : In the event that damage to packaging results in the release of cells or batteries, the spilled products should be promptly collected and segregated and the shipper should be contacted for instructions.

Design of positioning the battery pack in application and charger

To prevent the deterioration of the battery performance caused by heat, battery shall be positioned away from the area where heat is generated in the application and the charger.

Design of the Battery Pack

Be sure adopting proper safe device such as PTC specified type or model in Cell Specification. If you intend to adopt different safety device which is not specified in Cell Specification, please contact Samsung SDI to investigate any potential safety problem.

Be sure designing 2nd protective devices such as PTC & PCM at the same time to protect Cell just in case one protective device is fault.

Please contact following offices when you need any help including safety concerns.



Version No.	1.2
1	Version No.

Samsung SDI Emergency Contact Information

■ Samsung SDI Headquarter.

150-20, Gongse-ro, Giheung-gu, Yongin-si, Gyunggi-do, Korea Tel: +82-31-8006-3100, Fax: +82-31-210-7887

■ Samsung SDI Cheonan factory.

508, Sungsung-Dong, Cheonan City, Chungchongnam-Do, Korea Tel:(+82)70-7125-1834 Fax:(+82)41-560-3697

■ Samsung SDI America office.

18600 Broadwick Street Rancho Dominguez CA 90220 Tel:(+1)310-900-5205 Fax:(+1)310-537-1033

■ Samsung SDI Taiwan office.

Rm. 3010, 30F., 333, Keelung Rd. Sec. 1, Taipei, Taiwan Tel:(+886)2-2728-8469 Fax:(+886)2-2728-8480

■ Samsung SDI Malaysia factory.

Lot 635 & 660, Kawasan Perindustrian, Tuanku Jaafar, 71450 Sungai Gadut, Negeri Sembilan Darul Khusus, Malaysia Tel: (+60)6-677-6160, 6153