

# 昌 葧 股 份 有 限 公 司 Dr. POWER CORPORATION

# 零件規格書/承認書 SPECIFICATION FOR APPROVAL

CUSTOMER:					
DESCRIPTION : Polymer Li-ion battery					
MODEL: SL35	0827 65mAh				
CUSTOMER PART NO :					
APPROVED SIGNATURES					

Rev	Date	Description	Designed	Checked	Approved
Α	2022/6/1	Release		Po Chen	

臺北市北投區吉利街 131 號 3 樓

3F, NO. 131, JILI ST., PEITOU, TAIPEI, TAIWAN, R.O.C.

TEL: 886-2-2820-7419 · FAX: 886-2-2827-0348

DOC NO.: RD-SL350827-03145				
REV. : A/0				
CHEET		2 of 10		

# **AMENDMENT RECORDS**

# 修改记录表

Revision 版本	Description 描述	Date 日期	Prepared 制定	Approval 核准
A/0	Preliminary draft 首次发行	2021-07-19	杨聪聪	汤大明

 DOC NO.: RD-SL350827-03145

 REV.
 :
 A/0

 SHEET
 :
 3 of 10

# **CONTENTS**

1.	Scope 范围	4
2.	Model 型号:SL350827	4
3.	Specification 规格说明	4
4.	Safety Performance 安全性能	5
5.	Temperature applicability 温度适应性	5
6.	ESD 静电释放	5
7.	Cell Safety Criteria for Acceptance 电芯安全标准	6
8.	Warranty and product liability产品保证与责任	7
9.	Caution 警告	7
10.	Shipping Drawing 出货图样	8
11.	Pack part list 包装物料单	8
12.	PCM Specification 保护板规格	9

DOC NO.: <u>RD-SL350827-03145</u>				
<b>REV.</b> : <b>A/0</b>				
SHEET		4 of 10		

### 1. Scope范围:

This document describes the Product Specification of the Lithium-ion Polymer rechargeable battery SL350827 supplied by Shenzhen Jingxian Battery Technology Co., Ltd.

本规格书描述了由深圳敬贤电池科技有限公司生产的聚合物锂离子电池的产品性能。

### 2. Model型号: SL350827

### 3. Specification规格

No.	Items 项目	Specifications 规格		
3.1	Appearance 外观	The surface is clear and no scratch,no mechanical,match well with the main machine 表面干净无机械性刮伤		
3.2	Charge voltage 充电电压	4.35V		
3.3	Nominal voltage 标称电压	3.8V		
3.4	Nominal capacity 标称容量	65mAh		
3.5	Minimum capacity 最小容量	63mAh (0.2C discharge)		
2.6	Standard Charge(25±2℃)		.35V , 0.2C恒流充电至4.35V	
3.6	标准充电	Constant voltage 4.35V 0.02C	mA cut-off 恒压充电至0.02C截止	
3.7	Fast charge(25±2℃)	Constant current 1.0C mA to 4	.35V 1.0C恒流充电至4.35V	
3.1	快速充电		mA cut-off 恒压充电至 0.02C 截止	
3.8	Standard Discharge (25±2℃) 标准放电	Constant current 0.2CmA 3.0V 0.2C 恒流放电至 3.0V	Cut-off	
3.9	Fast Discharge(25±2℃) 快速放电	Constant current 1.0CmA 3.0V Cut-off 1.0C 恒流放电至 3.0V		
3.10	Operating temperature 工作温度	Charging 充电: 0°C ~ 10°C 0.2CmA/4.35V,0.02CmA cut-off 10°C ~ 45°C 1.0CmA/4.35V,0.02CmA cut-off Discharging 放电: -20°C ~60°C 0.2CmA/3.0V		
		-20°C~25°C	(12 months, ≥85%)	
	Storage (At 50% SOC and	-20℃ ~35℃	(3 months, ≥85%)	
	specified temp, recoverable	-20°C ~45°C	(1 month, ≥90%)	
3.11	capacity in % vs time.)	-20°C~60°C	(1 month, ≥80%)	
	储存(在50%的带电量下,可恢复	20±5°C is the recommended storage temperature		
	容量与时间的特性)	20±5℃为我司推荐的储存温度		
3.12	Cycle Life 循环寿命		t std charge / std discharge(25±2°C)	
3.13	Impedance 内阻	≤530mΩ		
3.14	Pack weight 成品重量	Approx.2.0g		
3.15	Delivery voltage 出货电压	≥3.9V		
3.16	Delivery capacity 出货容量	≥70%		
3.17	Warranty Time 保质期	12 Month		
3.18	Environment requirement 环境要求	RoHs		
3.19	Cell material system 电芯材料体系	High voltage and low tempera 钴酸锂高电压低温体系	ture system of lithium cobaltate	

DOC NO.: RD-SL350827-03145			
REV.	•		
SHEET		5 of 10	

### 4. Safety Protection Performance 安全保护性能

No.	Items 项目	Test Method and Condition 测量方法与条件	Criteria 判定标准
4.1	Over-Charge	At 20±5°C conditions, after fast-charging,	The appearance is normal, no
	Protection	use an external 5V power to charge the	explosion, no fire, no
	过充保护	battery and last for 24 hours, then check the	smoking, no leakage.
		appearance of battery.	外观正常,不爆炸,不起火,
		20±5℃条件下,快速充电至 5V 并保持 24h, 检	不冒烟,不漏液
		查电池的外观	
4.2	Over-Discharge	At 20±5°C conditions, discharge battery to 2.5V	The appearance is normal, no
	Protection	with 0.2C constant current, then discharge with	explosion, no fire, no
	过放保护	$30\Omega$ loading for 24 hours. Check the appearance	smoking, no leakage.
		of battery.	外观正常,不爆炸,不起火,
		20±5℃条件下,以 0.2C 恒流放电至 2.5V,保持	不冒烟,不漏液
		24h, 检查电池的外观	
4.3	Short-Circuit	After fast-charging, use a cable of $0.1\Omega$ resistance	The appearance is normal, no
	Protection	to short the battery for 24 hour. Then check the	explosion, no fire, no
	短路保护	appearance of battery.	smoking, no leakage.
		快速充电后,外接 0.1Ω电阻短路 24h,检查电	外观正常,不爆炸,不起火,
		池的外观	不冒烟,不漏液
		Cut circuit of resistance test the battery's voltage	
		after charging with 1C constant current for 5	
		seconds.	
		切断外接电阻后,测试电压后以 1C 恒流充电 5s	

### 5. Temperature Applicability(温度特性)

5.1. Discharge Performance at High Temperature 高温下放电特性

At  $55\pm2^{\circ}$ C conditions, keep the battery for 2hrs, discharge the battery to 3.0V with 0.2C constant current. After keep the battery 2hrs at  $20\pm5^{\circ}$ C, then check the appearance of battery. The discharge capacity is above 80% of original capacity. The appearance is no distortion, no explosion, no leakage.

在  $55\pm2$ ℃条件下保持 2h,以 0.2C 放电至 3.0V 后,在  $20\pm5$ ℃保持 2h,检查电池外观。充 80%的容量,电池不变形,不爆炸,不漏液。

5.2 Discharge Performance at Low Temperature 低温下放电特性

At -10±2  $^{\circ}$ C conditions, keep the battery for 2hrs, discharge the battery to 3.0V with 0.2C constant

current. After keep the battery 2hrs at  $20\pm5$  °C, then check the appearance of battery. The discharge capacity is above 85% of original capacity. The appearance is no distortion, no explosion,no leakage.

在- $10\pm2$  ℃条件下保持 2 h,以 0.2C 放电至 3.0V 后,在  $20\pm5$  ℃保持 2 h,检查电池外观。充 85%的容量,电池不变形,不爆炸,不漏液

#### 6. ESD(静电释放)

At direct discharge against the pins with  $\pm 4kv$  and over the housing with  $\pm 8kv$ .

在±4kv 的针脚或±8kv 外罩下放电

No damages are allowed. 不允许有损害

DOC NO.: <u>RD-SL350827-03145</u>

REV. : <u>A/0</u>
SHEET : <u>6 of 10</u>

# 7. Cell Safety Criteria for Acceptance 电芯安全接受标准

7. Cen Safety Criteria for Acceptance 电心女主接支标准				
Item 项目	State 状态	Test method 测试方式	Specification规格	
External Short-circuit Test 外部短路测试	Fully Charged 满充	Cell terminals are short-circuited to discharged state less than $0.1V$ or longer time with a resistance of $50m\Omega$ or less. Tests are to be conducted at room temperature. 在常温测试条件下,在电芯极耳用 $50m\Omega$ 的电阻进行长时间的短路,直至电压低于 $0.1V$	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	
Heating Test 热测试	Fully Charged 满充	The temperature of the oven is to be raised at a rate of $5\pm2$ $^{\circ}$ C/min. to a temperature of $130\pm2$ $^{\circ}$ C, and remains for 30 minutes at this temperature. 在烤箱中以 $5\pm2$ $^{\circ}$ C/min的加热速率至温度达到 $130\pm2$ $^{\circ}$ C, 保持 $30$ 分钟	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	
Crush Test 挤压测试	Fully Charged 满充	Crush between two flat plates. Applied force is about 13kN. 在两块平板之间用13kN力进行挤压,	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	
Impact Test 重物冲击	Fully Charged 满充	Impact between bar (15.8mm diameter) and 9 Kg falling material (at a height of 50 cm). Bar is laid across the center of the test sample. 将直径为15.8mm的铁棒放在电芯,9Kg的重物从50cm高度下落,铁棒穿过样品的中心位置	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	
Drop Test 跌落测试	Fully Charged 满充	Drop a fully charged cell onto a concrete floor from the height of 1.0 meters for 2 times. 满充后的电芯每个面从1m高处自由落下2次	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	
Vibration Test 振动测试	Fully Charged 满充	Vibrate the cell in tri-axial directions each for 90~100 min. in conditions of 10~55 Hz with amplitude 0.8 mm. 以10~55Hz的频率、振幅0.8mm,电芯在三维方向振动90~100min	NO EXPLOSION DEFORMATION AND NO FIRE 不爆炸变形, 不起 火	
Nail Test 针刺	Fully Charged 满充	The battery is fully charged in standard charging condition, Standby for 2 hour, a nail is penetrated vertically through the center of the cell (The diameter of the nail is 3.0mm.) 电池满充电后,用一根直径为3.0mm 的铁針垂直刺穿电芯	NO EXPLOSION AND NO FIRE. 不爆炸,不起火	

 DOC NO.:
 RD-SL350827-03145

 REV.
 :
 A/0

 SHEET
 :
 7 of 10

#### 8.0 Warranty and product liability 产品保证与责任

Warranty period of this product is 12months from delivery date.保质期为出货后的 12 个月

( when the customer using it in the host, need charge it as bellow 8.13 requirement )当客户使用后,需遵循 8.13 的要求 You are kindly requested to use the battery, which is delivered from JX in strict accordance with the specification, and remarks include at the end of the document. Due to improper usage of the battery, an accident or a fire may occur due to the battery generating heat, catching fire or rupture, smoke.

JX will not guarantee against any accidents occurring due outside those written in this specification.

您必须严格遵守深圳市敬贤电池科技有限公司规格书和文件后面的注释使用电池,由于误用会引起电池过热,发生火灾或爆炸。对没有按照规格书进行操作所造成的任何事故,敬贤不负担任何责任。

#### 9.0 Caution!警告

In order to prevent the battery possibly occurs leaks, over heat, swollen, please note the preventive measure. 为避免电池出现漏液,过热,鼓胀,请注意以下事项

#### Handling Precautions and Guideline:操作方法与原则

- 9.1 When charge please select the lithium-polymer battery special battery charger.请使用锂离子电池专用充电器
- 9.2 Strictly prohibits inverting the cathode use battery. 严禁颠倒正负极使用电池。
- 9.3 Strictly prohibits directly connect battery to power source plug 严禁将电池直接接入电源插座
- 9.4 Please do not throw the battery to water or put into heater 禁止将电池丢于火或加热器中。
- 9.5 Strictly prohibits plunging the battery in sea water or water, when battery do not use, please store battery in the cool-dry environment. 严禁将电池浸入海水或水中, 保存不用时, 应放置于阴凉干燥的环境中。
- 9.6 The prohibition in strong static electricity and strong magnetic field place use, otherwise is easy to destroy the battery PCBA。禁止在强静电和强磁场的地方使用, 否则易破坏电池安全保护装置, 带来不安全的隐患。
- 9.7 The prohibition puts the battery nearby the hot high temperature source, like the fire, the heater and so on use and leaves alone 禁止将电池在热高温源旁, 如火、加热器等使用和留置。
- 9.8 The prohibition directly connects the battery cathode with the metal to short-circuit。禁止用金属直接连接电池正 负极短路
- 9.9 The prohibition rap or throws, steps on the battery and so on 。禁止敲击或抛掷、踩踏电池等
- 9.10 Forbids directly to weld the battery and pierces the battery with the nail or other sharp weapons。禁止将电池与金属,如发夹、项链等一起运输或贮存
- 9.11 If the battery sends out the unusual smell, gives off heat, the distortion or appears any exceptionally, immediately moves the battery from the installment or the battery charger to and stops using 。如果电池发出异味、发热、变色、变形或使用、贮存,充电过程中出现任何异常,立即将电池从装置或充电器中移离并停用
- 9.12 If the battery occurs leaks, the electrolyte enters eye, please do not have to rub scratches, the application clear water flushing eye, and delivers the medical treatment otherwise to be able immediately to injure the eye 。如电池泄露,电解液进入眼睛,请不要揉擦,用清水冲洗眼睛,立即送医治疗,否则会伤害眼睛
- 9.13 When battery long-term storage, or assembly in the host, suggest customer should take every 6months carry on one time charge and discharge and recharge it to half-charge state (3.7-3.9V)(the method: 0.2CmA charge and discharge).当电池长时间不使用时,建议每6个月对电池进行一次充放电,并充电至半电(3.7V~3.9)
- 9.14 Abandon the battery to wrap up the electrode using the insulating paper, prevented the battery short-circuits. 废弃之 废弃电池应用绝缘纸包住电极
- 9.15 Do not decompose the battery.禁止拆解电池


# PRODUCT SPECIFICATION

产品说明书

DOC NO.: <u>RD-SL350827-03145</u>

REV. : <u>A/0</u>
SHEET : <u>8 of 10</u>

### 10. Shipping Drawing 成品图纸



QR code:ABCDEFGHIJKL

ABC: MI code工艺文件编号

D: Year年 EF: Week 周 G: Day星期

HIJKL: Serial number 流水号

## 11. Pack parts list 物料清单

No	Name	Type or Specification	Qty	Unit	Remark
11.1	Cell	SL350827-65mAh 3.8V	1	PCS	
11.2	Capacity	SMD-0402/0.1uF-20%/+80% 16V	1	PCS	
11.3	Resistance	SMD-0402/470Ω±5%	1	PCS	
11.4	Resistance	SMD-0402/2KΩ±5%	1	PCS	
11.5	IC	DFN 2*2DD-6L/BM197-VFAX-DE	1	PCS	
11.6	PCB	JZX-6030	1	PCS	
11.7	Wire	UL3302 32#(red,balck)	2	PCS	

DOC NO.: <u>RD-SL350827-03145</u> REV. : A/0

SHEET : <u>9</u> of <u>10</u>

### 12. PCM Specification保护板规格

12.1 Scope 范围


The specification is applied to the protection of lithium-ion battery from overcharge, over discharge, over current and short-circuit.

此规格书适用于锂离子电池的过充、过放、短路保护功能

- 12.2 Model 型号: SL350827
- 12.3 Main organ 主要元件:


IC:BM197-VFAX-DE


12.4 Application Circuit 线路板原理图




#### 12.5 PCB Layout布局图


Top Layer





Bottomp Layer





#### 12.6 Pad description and parts location diagram:焊点说明

Item 项目	Description 描述	Item 项目	Description 描述
P+	Battery pack positive terminal 电池正极端子	P-	Battery pack negative terminal 电池负极端子
B+	Connect to cell positive 连接电芯正极	B-	Connect to cell negative 连接电芯负极

DOC NO.: <u>RD-SL350827-03145</u>

REV. : <u>A/0</u>

SHEET : 10 of 10

12.7 Electricity parameter (Environment temperature 25℃) 电性能参数:

Item 项目	Name 名称	Term	Min	Typical	Max	Units
Voltage 电压	Over charge detection voltage 过充保护截止电压		4.4	4.425	4.45	V
	Overcharge detection delay time 过充保护延迟时间		600	/	1800	mS
	Over charge release voltage 过充保护恢复电压		4.175	4.225	4.275	V
	Over discharge detection voltage 过放保护截止电压		2.73	2.8	2.87	V
	Over discharge detection delay time 过放保护延迟时间		/	/	175	mS
	Over discharge release voltage 过放保护恢复电压		2.8	2.9	3.0	V
Current 电流	Operation of current consumption 静态电流		/	/	7	μА
	Over discharge current detection 放电过流保护电流		0.25		1.45	A
	Over discharge current detection delay time 放电过流保护时间		5	/	12	mS
	Short circuit protection 短路保护		OK			
	Short circuiting detection delay time 短路保护延迟时间		220	300	380	us
NTC 热敏电阻		/				
ID 编号		/				
0V battery charge function OV 电池充电功能		Available 适用				
Resistance 电阻	PCB Resistance 保护板电阻	≤60				mΩ

### 13、Battery pack packaging requirements /电池组的包装要求.

Figure, size, color flag comply with GP/T 191-2000 requirements. Or according to JX standard.标志的图形、尺寸、颜色符合 GP/T 191-2000 的要求。或按照敬贤电池科技有限公司标准执行。 Any matters that this specification doesn't cover should be conferred between the customer and JX. 任何本规格书中未提及的事项,需要经双方协商确定,如下图:

